

Quick Start Guide - Pillar Blend (PB)

Pillar Blend (PB)




1. WICK a clean, conditioned* mold.


**Should be conditioned with a soybean or vegetable oil.*




2. MELT PB to at least 155° F (68.3°C).



3. Use PB COMPATIBLE fragrances and dyes.



4. Generally POUR at 140°F (60°C).



5. COOL ideally at 68-75°F (20-23.9°C), spaced 1/2 inch apart.



**Please refer to the full product instructions available at www.ngiwax.com